



# ODORLESS FINASOL

## (Odorless Mineral Spirits)

**ODORLESS FINASOL** meets the general requirements for mineral spirits with solvent and boiling range typical of a Stoddard Solvent. Its high flash point (T.C.C. method) makes it a desirable product for use in paints, varnishes, enamels and other coating materials. It can also be used in chemical specialties such as polishes, dressings, preservatives coating, degreasers, and equipment parts cleaning.

**ODORLESS FINASOL** should be used with adequate ventilation. Excessive inhaling of vapors or prolonged contact with skin may be harmful, and are harmful or fatal if swallowed.

The Threshold Limit Values are 100 parts of vapor per million air for **ODORLESS**

**FINASOL.** This value is the maximum average atmospheric concentration to which workers may be exposed for an eight-hour working day without injury to health.

**ODORLESS FINASOL** is classified as flammable or combustible and must be kept away from sparks, heat or open flames. Containers should be kept closed when not in use.

**ODORLESS FINASOL** meets the following specifications:

- ASTM D 235 (Type III) Mineral Spirits
- TT-T-295—Paint Thinner, Mineral Spirits, Odorless
- TT-T-291 (Type III) Thinner, Paint, Mineral Spirits, Regular and Odorless

### TYPICAL CHARACTERISTICS

Product Code	na
Specific Gravity (ASTM D-1298)	0.7603
Weight, Pounds per Gallon 60°F/15.6°C	6.33
Color	Water White
Flash Point (T.C.C.) minimum	110F/43°C.
Odor	Very low
Kauri Butanol Value	28
Aniline Point	160°F/71°C
Aromatics by UV, wt%	<0.5
ASTM. Distillation (98% recovery) °F	
I.B.P.	340
50%	365
Dry Point	395

The above data is subject to usual manufacturing variation. For more information and availability, call 1-800-442-LUBE.  
6/15/04