

ZENIPLX[®]

Aluminum Complex EP Greases

Zeniplex Aluminum Complex Grease is a high performance EP lubricant with excellent mechanical stability, oxidation resistance and anti-wear characteristics. Superior in resistance to heat, moisture and most chemicals, it is formulated for use in tough, wet, hot applications. Zeniplex is industry's "A to Z" premium grease for general applications and is also authorized by the USDA for use where there is no possibility of food contact in federally inspected meat and poultry plants.

Features

- USDA H-2*
- Aluminum Complex
- Extreme Pressure Water Resistant

* Authorized by USDA for use in inspected meat and poultry plants where no contact with edible product is possible.

Performance

- Assures government compliance
- Stable to shear and high temperature resistant
- Lubricates heavy loads
- Reduces washout in wet applications

Applications

General purpose and heavy-duty applications, up to 325°F in plain and anti-friction bearings with frequent resupply, slides and way, automatic systems (NLGI grade 0). Zeniplex grease is compatible with lithium complex greases. Some softening with other grease types can occur when they are mixed. It is recommended that old grease should be flushed from the bearings when possible.

Typical Properties	Zeniplex 0	Zeniplex 1	Zeniplex 2
Product Code #	800138	800151	800159
Operating Range, °F	0-325	0-325	0-325
Penetration, worked, (ASTM D-217)	355-385	310-340	265-295
NLGI Grade	0	1	2
Dropping Point, °C, (ASTM D-2265) minimum	238	244	250
Appearance	Smooth, Brown	Smooth, Brown	Smooth, Brown
Water Washout, % loss, 175°F, (ASTM D-1264)	N/A	7.5	4.2
Rust Test (ASTM D-1743)	Pass	Pass	Pass
Oxidation, psi loss, 100 hrs., (ASTM D-942)	-5 max.	-5 max.	-5 max.
Copper Corrosion (ASTM D-130)	Max 1b	Max 2a	Max 2a
Timken OK Load, lbs. (ASTM D-2509)	50	50	50
4-Ball Weld Load, kg. (ASTM D-2596)	280	280	280
4-Ball Wear, 40 kg., (ASTM D-2266), mm	0.53	0.53	0.53
Base Oil Properties			
Kinematic Viscosity @ 40°C	220	220	220
Flash Point, C.O.C., °F, (ASTM D-92)	450	450	450
Pour Point, °F, (ASTM D-97)	10	10	10

Revised 10/06 WHC

TOTAL Lubricants USA, Inc.

TOTAL Lubricants USA, Inc. with a policy of continuous improvement, reserves the right to change specifications as our technology progresses. We are not responsible for the misuse and/or misapplication of our products. ©2002 All rights reserved.

Linden, NJ 07036
5 North Stiles Street
908.862.9300 800.526.4127

Rockingham, NC 28379
709 Airport Road
800.323.3198

Knoxville, TN 37914
3315 Riverside Drive
800.323.3198